

## SOLUTIONS ENVIRONMENTAL PROTECTION, INC.

1567 W. South Airport Rd. Traverse City, Michigan 49686

The Liner Company

Phone | 800-0K-LINER Fax | 231-943-2270

www.geomembrane.com

TYPICAL APPLICATIONS:

Landfill Liners

Landfill Closures

Reservoirs

Sewage Lagoons

Soil Remediation

Industrial Waste Ponds

## 40 mil PVC Geomembrane Specifications

PVC liners fabricated by EPI are a single-ply construction with Polyvinyl Chloride as the principle polymer. Only first quality virgin resins are used and all materials meet or exceed the requirements of ASTM D7176 Standard Specification for PVC geomembranes used in buried applications.

EPI utilizes statistical process control (SPC) to ensure the integrity of each panel produced. Samples from actual factory seams are removed during the welding process for a rigorous, proven testing procedure that assures you of the highest quality factoryfabricated PVC geomembranes available.

PVC Liners are fabricated by EPI in panels, accordion-folded in both directions, and packaged for shipment to your site for quick, easy installation to save you time and money.

Thickness $\pm 5\%$ Specific Gravity (min)	ASTM D-5199 ASTM D-792	.040" 1.20
Tensile (lb/in-width, min)	ASTM D-882	97
Elongation at Break (% min)	ASTM D-882	430
Modulus (Ib/in-width, min)	ASTM D-882	40
Tear Resistance (lb/in, min) Resistance to Soil Burial (% change, max)	ASTM D-1004 ASTM G-160	10
<ol> <li>Breaking Factor</li> <li>Elongation At Break</li> <li>Modulus at 100% Elong</li> </ol>	ation	5 20 20
Impact Cold Crack (°C) Dimensional Stability (% change, max)	ASTM D-1790 ASTM D-1204 (212°F/15 min.)	-29 3
Water Extraction (%,max) Volatile Loss (%, max) Hydrostatic Resistance (psi, min) Plasticizer Min Ave Molec W	ASTM D-1239 ASTM D-1203(A) ASTM D-751(A) /t ASTM 2124	0.20 0.50 120 400
Factory Fabricated Seams:Peel Strength (lbs/in, min)ASTM D-740815Shear Strength (lbs/in, min)ASTM D-740877.6		

These data are based on tests believed to be reliable. However, these are laboratory tests that may not simulate actual use conditions. They are provided for your informational purposes only. No warranty, express or implied, including any other further warranty of fitness for a particular purpose or merchantability, is made by this promotional literature.

Preserving water resources for future generations